



Arianoplast 4 Terrasses de Bretagne, ZA Terrasses de la Sarre
57400 SARREBOURG +336 52 04 34 31

ARIANEPLAST ASA Characteristics ASA

PROPERTIES	ASTM TEST METHOD	TEST CONDITION	UNIT	GENERAL
				ASA
熔融指數 Melt Flow Index	D1238	220 °C, 10 Kg	g/10 min	23
比重 Mass Density	D792	23 °C	-	1.07
硬度 Hardness	D785	-	R Scale	105
拉伸強度 (屈服) Tensile Strength (Yield)	D638	6 mm/min	Kg/cm ²	440
			lb/in ²	6240
延伸率 Tensile Elongation	D638	6 mm/min	%	55
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	650
			lb/in ²	9180
彎曲彈性模數 Flexural Modulus	D790	2.8 mm/min	10 ⁴ Kg/cm ²	2.2
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	15
			ft-lb/in	2.7
		3.2 mm, 23°C	Kg-cm/cm	16
			ft-lb/in	2.9
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	105
			°F	221
熱變形溫度 Heat Distortion Temp.	D648	Annealed	°C	95
			°F	203
		Unannealed	°C	85
			°F	185
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB